



TEST REPORT

No. : SHIN1504013699PS

Date : Apr 16, 2015

Page: 1 of 2

CUSTOMER NAME: BEC INDUSTRIAL (SHANGHAI) CO.,LTD
ADDRESS: NO.5050, LONGWU ROAD, MINHANG DISTRICT, SHANGHAI, CHINA
200241

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : Asbestos-free Calcium Silicate
Manufacturer : BEC Industrial (Shanghai) Co., Ltd
Date of Receipt : Apr 03, 2015
Testing Start Date : Apr 03, 2015
Testing End Date : Apr 16, 2015
Test result(s) : For further details, please refer to the following page(s)

Signed for
SGS-CSTC Standards Technical
Services (Shanghai) Co., Ltd.

Zano Lai

Zano Lai
Authorized signatory



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China 201319 t(86-21) 61196300 f(86-21) 68183122/68183920 www.sgs.com
中国·上海·浦东康桥东路1159弄69号 邮编: 201319 t(86-21) 61196300 f(86-21) 68183122/68183920 e sgs.china@sgs.com

TEST REPORT

No. : SHIN1504013699PS

Date : Apr 16, 2015

Page: 2 of 2

Test Item: Tumbling Friability

Test Method: ASTM C421-08(R2014)


Lab Environmental Condition: 23±1°C, 50±5%RH

Test Result:

Test item	Test method	Test result	Requirement in ASTM C533-13	Verdict
Mass loss by tumbling after first 10 minutes (%)	ASTM C421-08(R2014)	8.4	≤20	Pass
Mass loss by tumbling after second 10 minutes (%)		15.6	≤40	Pass
Remark	Specimen dimensions: 25.4mm×25.4mm×25.4mm, 12pcs.			

Statement: Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Sample Photo:



***** End of report*****



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China 201319 t(86-21) 61196300 f(86-21) 68183122/68183920 www.sgsgroup.com.cn
 中国·上海·浦东康桥东路1159弄69号 邮编: 201319 t(86-21) 61196300 f(86-21) 68183122/68183920 e sgs.china@sgs.com